

# Urochem 515

## ONE-PART 15 SHORE A' HYBRID SEALANT

### DESCRIPTION

**Urochem 515** is a high-performance low modulus moisture curing sealant, based on hybrid technology which is both isocyanate and VOC free. It has a good cure rate, excellent moisture, and oxidation resistance, and exhibits excellent adhesion to cementitious substrates, asphalt, brick, stone, steel, wood, and ceramic tiles. It has an extremely low modulus and high elongation and is recommended for use in areas where extreme movement is anticipated. (50% of initial joint width)

### PRODUCT APPLICATION

- **Urochem 515** can be used as a joint sealer and crack filler on various surfaces and will provide excellent movement accommodation. It can be used externally in road joints if it is recessed by 5mm to avoid tyre wear. It provides medium chemical, wear and corrosion resistance, while at the same time curing to a 15 Shore A hardness (+/- 5 Shore A). A degree of colour change with time is to be expected. It is not recommended for use in water retaining structures.
- If applied to natural stone, we recommend the use of **Urochem 105** Primer. **Urochem 515** is overcoatable, however the coating will crack as it will not accommodate the same movement as the sealant. It is recommended that a compatibility test is done prior to application or painting.

### SURFACE PREPARATION

All surfaces to be clean sound and dry, free of moisture, dust, laitance, and oil. If used in severe or damp conditions prime with **Urochem 106**.

### APPLICATION

- Place sausage in the barrel gun, cut end off sausage and fit the nozzle; trim the tip to suit the joint spacing to be filled. Insert backing rod to the correct depth. Gun the product into prepared joints and smooth with a dry spatula. The joint width should be designed to accommodate the expected movement, the joint ratio for 6 – 10mm wide joints is 1:1 thereafter a ratio of 2:1 should be respected.
- **Note a minimum width of 6mm and a maximum of 50mm should be adhered to.** A backing cord/bond breaker should be used depending on application, to prevent three-sided adhesion.

### CLEANING

Clean all tools and equipment immediately after use with **Urochem 901**, as the cured material is very difficult to remove.

### SAFETY

Contact with the skin should be avoided by wearing gloves, eye protection and protective clothing. In case of eye contact wash well and obtain medical advice.

### APPROXIMATE COVERAGE

Joint Dimension:	LM per 600ml:
6 x 6mm	16.6
8 x 8mm	9.38
10 x 10mm	6
12 x 6mm	8.33
15 x 8mm	5



**Urochem Trading (Pty) Ltd**

Unit XP2, AEL Industrial complex, Cnr Ecqip and Weighbridge  
Modderfontein, Gauteng; 1645

(+27) 11 608 2073 • [www.urochem.co.za](http://www.urochem.co.za)

# Urochem 515

## ONE-PART 15 SHORE A' HYBRID SEALANT

### TYPICAL PROPERTIES – AS PER UROCHEM QC

The below properties are based on in-house testing methodologies.

<b>Mixing Ratio</b>	Single component
<b>Skin over time</b>	1-2 Hrs dependant on RH, temp & thickness
<b>Practical Cure</b>	± 2mm per day dependant on RH & temp
<b>Hardness</b>	± 15 Shore A
<b>Movement accommodation</b>	50 % of initial joint width
<b>Tensile strength</b>	0.5 – 1 Mpa
<b>Colour</b>	Grey, colours available on order
<b>Density</b>	1.4 Cured
<b>Shelf Life</b>	12 Months
<b>Application Temp.</b>	5 – 35°C
<b>Service Temp.</b>	-10°C to +60° C
<b>Pack Size</b>	600 ml sausages
<b>Cleaning</b>	<b>Urochem 901</b>
<b>Storage</b>	Store in a cool dry place

The information and recommendations relating to the application and end-use of **Urochem Trading (Pty) Ltd.** products, are given in good faith based on our current knowledge and experience of our products. **Urochem Trading (Pty) Ltd.** cannot accept any liability either directly or indirectly arising from the use of our products, as we have no direct or continuous control over where and how our products are stored and applied. Field service provided does not constitute supervisory responsibility. Users must test the efficacy of the product for their specific application, as no guarantee is expressed or implied. **Urochem Trading (Pty) Ltd.** reserves the right to change the properties of its products at any time without notice therefore users must always refer to the most recent issue of the specific Technical Data Sheet or contact one of our Technical Advisors before use.

### FOR PROFESSIONAL USE ONLY



### Urochem Trading (Pty) Ltd

Unit XP2, AEL Industrial complex, Cnr Ecqip and Weighbridge  
Modderfontein, Gauteng; 1645

(+27) 11 608 2073 • [www.urochem.co.za](http://www.urochem.co.za)