

Urochem 299 LV

TWO-PART POURABLE POLYURETHANE JOINT SEALANT – “WASTEWATER TREATMENT PLANTS”

DESCRIPTION

Urochem 299 LV is a two-component low viscosity, semi self-levelling sealing compound based on a polyether polyurethane. It is blended with fillers and a chemical curing agent, which reacts after mixing to form a durable rubber like seal. This sealant is highly elastic and is able to withstand continuous extension and recovery. It may be used with most common building materials such as concrete, plaster, brick, and stone. It exhibits superior resistance to abrasion, ultraviolet light and ozone making it suitable for exterior use. Due to its excellent water resistance and adhesion and resistance to biodegradation, it forms the ideal material for use in sewage treatment plants. **Urochem 299 LV** cannot be used on vertical surfaces due to its low viscosity.

PRODUCT APPLICATION

- To form a long-lasting water and weatherproof seal in horizontal movement joints which are subject to continuous cyclic movement.
- Typical applications include horizontal expansion joints in floors, drainage channels and sewage treatment plants.

SURFACE PREPARATION

The correct preparation of the joint faces is absolutely essential to the satisfactory performance of the sealant. All surfaces should be clean, sound, and dry, and laitance or surface contamination should be removed by thorough wire brushing, grinding or grit blasting. Vacuum or blow with compressed air to ensure thorough removal of dust. Metal surfaces should be free of mill scale and rust and mild steel treated with a suitable anticorrosive primer.

JOINT DESIGN

- The recommended minimum joint dimension is 6 x 6mm, but where possible we recommend a 10 x 10mm joint.
- For joints ranging from 6mm to 10mm wide, we recommend a width to depth ratio of 1:1, for anything wider a 2:1 width to depth ratio should be maintained.
- In water retaining structures a 1:1 ratio should be maintained due to Hydrostatic pressure and cyclic movement.
- These ratios provide the optimum geometry to allow movement to occur within the joint without placing excessive force on the joint faces.
- Joint faces should be parallel, and the joint width should be at least four times the anticipated movement.
- When placing the sealant, the joint opening should if possible be central to its maximum compression/expansion cycle.



Urochem Trading (Pty) Ltd

Unit XP2, AEL Industrial complex, Cnr Ecqip and Weighbridge
Modderfontein, Gauteng; 1645

(+27) 11 608 2073 • www.urochem.co.za

Urochem 299 LV

TWO-PART POURABLE POLYURETHANE JOINT SEALANT – “WASTEWATER TREATMENT PLANTS”

BOND BREAKER

To ensure proper movement of the joint a bond breaker must be used at the base of the joint. Where a backing material such as polyethylene foam rod is used to ensure the correct joint geometry, a bond breaking tape is not required. For water retaining structures care must be taken to comply with the design requirements as set by the project engineer.

PRIMING

- **Urochem 102 Silane Primer** should be used on glass, ceramics and sound masonry and brick surfaces not subjected to water immersion.
- For water retaining structures, porous or friable surfaces or where severe conditions are expected use **Urochem 101, 106 or 614**. Refer to relevant data sheet.

MIXING

- **Urochem 299 LV** is supplied in a two-part kit, base, and activator in separate tins.
- Transfer the total quantity of activator into the base component and mix thoroughly using a slow speed electric drill fitted with a flat blade stirrer.
- Scrape down the sides of the can and the base and remix until the colour is uniform and free from streaks.
- Thorough mixing is essential and should take 5 to 10 minutes.

APPLICATION

Pour into primed joint's using a suitable container and level surface using a scraper.

CLEANING

Clean all tools and equipment with **Urochem 901** before curing of the sealant has occurred.

SAFETY

Contact with skin should be avoided by wearing gloves and protective clothing. The activator is slightly caustic. In case of eye contact wash well and obtain medical advice.



Urochem Trading (Pty) Ltd

Unit XP2, AEL Industrial complex, Cnr Ecqip and Weighbridge
Modderfontein, Gauteng; 1645

(+27) 11 608 2073 • www.urochem.co.za

Urochem 299 LV

TWO-PART POURABLE POLYURETHANE JOINT SEALANT – “WASTEWATER TREATMENT PLANTS”

TYPICAL PROPERTIES – AS PER UROCHEM QC

The below properties are based on in-house testing methodologies.

Mixing Ratio	Two component – mix as supplied – Do not part mix
Pot Life	1 Hour @ 25°C
Tack Free	3 Hours
Full Cure	7 Days
Colour	Grey – Other colours available on order
Hardness	± 25 Shore A
Movement accommodation	± 25%
Chemical resistance	Most dilute chemicals – Not aggressive chlorinated water
Density	1,53 g/cm ³
Theoretical coverage	See Material Usage Guide below
Shelf Life	6 Months, depending on storage conditions
Application Temp.	5 to 35°C
Service Temp.	-10 to 90°C
Pack Size	2 Lt Kits
Cleaning	Urochem 901
Storage	Store in a cool dry well ventilated place away from heat & sunlight

MATERIAL USAGE ESTIMATING GUIDE

(No allowance made for wastage)

		Joint width in mm									
		6	8	10	12	15	20	25	30	35	40
Joint depth in mm	6	27	20,8	16,6	13,8						
	8		15,6	12,5	10,42	8,3					
	10			10	8,3	6,6	5				
	12				6,9	5,5	4,2	3,3			
	15					4,4	3,3	2,6	2,2		
	20						2,5	2	1,6	1,4	1,2
	25							1,6	1,3	1,1	1
	30								1,1	0,9	0,8
	35									0,8	0,7
	40										0,6
Lm per Litre, excluding wastage											



Urochem Trading (Pty) Ltd

Unit XP2, AEL Industrial complex, Cnr Ecqip and Weighbridge
Modderfontein, Gauteng; 1645

(+27) 11 608 2073 • www.urochem.co.za

Urochem 299 LV

TWO-PART POURABLE POLYURETHANE JOINT SEALANT – “WASTEWATER TREATMENT PLANTS”

CHEMICAL RESISTANCE

Chemical:	Result
Acetic Acid (10 %)	I
Acetic Acid (25 %)	NR
Ammonium Hydroxide Solution (0,88 %)	I
Ammonium Nitrate (50 %)	I
Ammonium Sulfate Solution (50 %)	R
Boric Acid Solution (Saturated)	NR
Chromic Acid (10 %)	NR
Citric Acid (20 %)	NR
Cresol (5 %)	I
Formic Acid (40 %)	NR
Glycerol	R
Hydrochloric Acid (conc)	NR
Lactic Acid (25 %)	NR
Maleic Acid (30 %)	NR
Mineral oil	I
Ozone	NR
Nitric Acid (30 %)	NR

Chemical:	Result
Nitric Acid (70 %)	NR
Phenol	I
Phosphoric Acid (50 %)	NR
Phosphoric Acid (90 %)	NR
Propanol	I
Sodium Hypochlorite	NR
Sodium hydroxide (30 %)	I
Sodium hydroxide (50 %)	NR
Sugar solution (saturated)	R
Sulphuric Acid (30 %)	NR
Sulphuric Acid (70 %)	NR
Sulphuric Acid (98 %)	NR
T.E.A. (Saturated)	I
UREA (30 %)	I
Chlorinated compounds	NR

R = Compatible, I = Intermediate, NR = Not recommended

Urochem 299 shows very good bacterial resistance.

The information and recommendations relating to the application and end-use of **Urochem Trading (Pty) Ltd.** products, are given in good faith based on our current knowledge and experience of our products. **Urochem Trading (Pty) Ltd.** cannot accept any liability either directly or indirectly arising from the use of our products, as we have no direct or continuous control over where and how our products are stored and applied. Field service provided does not constitute supervisory responsibility. Users must test the efficacy of the product for their specific application, as no guarantee is expressed or implied. **Urochem Trading (Pty) Ltd.** reserves the right to change the properties of its products at any time without notice therefore users must always refer to the most recent issue of the specific Technical Data Sheet or contact one of our Technical Advisors before use.

FOR PROFESSIONAL USE ONLY



Urochem Trading (Pty) Ltd

Unit XP2, AEL Industrial complex, Cnr Ecqip and Weighbridge
Modderfontein, Gauteng; 1645

(+27) 11 608 2073 • www.urochem.co.za