

Urochem 340

HIGH STRENGTH, FREE FLOWING EPOXY GROUT

DESCRIPTION

Urochem 340 is a three component, solvent free epoxy resin grout formulated to withstand static and dynamic loads in a wide variety of applications. It is easily mixed with the supplied clean, dry aggregate to produce a pourable consistency grout.

TYPICAL APPLICATIONS

- Crane rails.
- Base plates for machines subject to static or dynamic forces.
- Structural filling of holes and cavities in concrete.
- Bridge bearings.

ADVANTAGES

- No priming required.
- Excellent flow characteristics.
- Long pot-life.
- High tensile, flexural, and compressive strength.
- Excellent adhesion to steel and concrete.
- Rapid installation and strength gain.
- High resistance to dynamic loads and chemical attack.
- Tolerant to damp surfaces.

SURFACE PREPARATION

Concrete surfaces should be clean sound and dry, free from laitance, paint, oil, grease, shutter oil and any residual curing compounds. Metal surfaces or components to be bedded, should be free from any rust, scaling, or paint. Formwork should be wrapped in polythene to ensure a clean release.

MIXING

Do not split kits. Mix with a slow speed drill fitted with a flat paddle. Add the contents of the activator to the base component in a suitable mixing vessel, ensuring complete transfer of both resin components. Mix for one minute before slowly adding aggregate and continue mixing until a free flowing, pourable lump free consistency is achieved.

PLACING / APPLICATION

Allow to stand for 5min before pouring into the prepared area in such a manner that it has the shortest distance to flow. For long pours a suitable head of pressure may be required. Ensure the area to be grouted is not completely sealed, and any displaced air can be expelled. Pour continuously from one side. Allow the grout to set prior to removal of formwork (normally after 6 hours). Where placement exceeds 3 x 5 Lt kits, application should be carried out in layers. Successive layers to be applied after 6-hour intervals.



Urochem Trading (Pty) Ltd

Unit XP2, AEL Industrial complex, Cnr Ecqip and Weighbridge
Modderfontein, Gauteng; 1645

(+27) 11 608 2073 • www.urochem.co.za

Urochem 340

HIGH STRENGTH, FREE FLOWING EPOXY GROUT

CHEMICAL RESISTANCE

Urochem 340 has excellent corrosion resistance to most common corrosive chemicals.

- Dilute and concentrated alkalis, Oil and petrol, Ammonia, Formaldehyde
- Saline solutions, Mineral oil, vegetable, and animal fats.

CLEANING

Clean all equipment promptly with **Urochem 901**. Any excess cured material will have to be mechanically removed.

HEALTH AND SAFETY

As with all chemical products, care should be taken during use and storage to avoid contact with eyes, mouth, skin, and foodstuffs (which can also be tainted with vapor until product is fully cured or dried). Treat splashes to skin and eyes immediately. If accidentally ingested, seek medical attention. Reseal containers after use. For specific storage and disposal instructions refer to the Material Safety Data Sheet.



Urochem Trading (Pty) Ltd

Unit XP2, AEL Industrial complex, Cnr Ecqip and Weighbridge
Modderfontein, Gauteng; 1645

(+27) 11 608 2073 • www.urochem.co.za

Urochem 340

HIGH STRENGTH, FREE FLOWING EPOXY GROUT

TYPICAL PROPERTIES – AS PER UROCHEM QC

The below properties are based on in-house testing methodologies.

Mixing Ratio	Three component - mix as supplied - Do not part mix
Pot Life	± 60 Min @ 25°C
Practical Cure	6 Hrs @ 25°C
Full Cure	7 Days
Compressive strength (Filled)	>80 Mpa @ 25°C
Tensile strength (Filled)	>10 Mpa @ 25°C
Flexural Strength (Filled)	>25 Mpa @ 25°C
Colour	Amber
Solids Content	100%
Theoretical Coverage	1m ² per Lt per mm thick
Shelf Life	12 Months
Application Temp.	5 to 35°C
Pack Size	5 Lt kit
Cleaning	Urochem 901
Storage	Store in a cool dry place - Do not freeze

The information and recommendations relating to the application and end-use of **Urochem Trading (Pty) Ltd.** products, are given in good faith based on our current knowledge and experience of our products. **Urochem Trading (Pty) Ltd.** cannot accept any liability either directly or indirectly arising from the use of our products, as we have no direct or continuous control over where and how our products are stored and applied. Field service provided does not constitute supervisory responsibility. Users must test the efficacy of the product for their specific application, as no guarantee is expressed or implied. **Urochem Trading (Pty) Ltd.** reserves the right to change the properties of its products at any time without notice therefore users must always refer to the most recent issue of the specific Technical Data Sheet or contact one of our Technical Advisors before use.

FOR PROFESSIONAL USE ONLY



Urochem Trading (Pty) Ltd

Unit XP2, AEL Industrial complex, Cnr Ecqip and Weighbridge
Modderfontein, Gauteng; 1645

(+27) 11 608 2073 • www.urochem.co.za