

Urochem 535

ONE-PART 35 SHORE A' HYBRID SEALANT AND ADHESIVE

DESCRIPTION

Urochem 535 is a thixotropic, VOC free, moisture curing, hybrid sealant/adhesive. It is a filled, moisture and oxidation resistant, mastic that exhibits excellent adhesion to cementitious, steel, wood, ceramic, aluminium, brick, and various other substrates. (Does not bond well to Stainless steel without a primer)

PRODUCT APPLICATION

- Urochem 535 can be used as a general joint sealer on low movement joints, as a crack filler on cementitious surfaces, as well as an adhesive on a wide range of substrates. It provides medium chemical, wear and corrosion resistance, while at the same time curing to a 35 Shore A hardness (+/- 5 Shore A). A degree of colour change with time is to be expected.
- ***It is not recommended for use in water retaining structures.***
- **Urochem 535** is overcoatable, however the coating will crack as it will not accommodate the same movement as the sealant.
- It is recommended that a compatibility test is done prior to application or painting.

SURFACE PREPARATION

All surfaces to be clean, sound, and dry, free of moisture, laitance, oils, and dust.

APPLICATION

- Ensure correct joint preparation before placing the sausage in the long barrel gun, cut end off sausage and fit the nozzle; trim the tip to suit the joint spacing to be filled before gunning the product into prepared joints.
- The adhesive may be smoothed and finish off with soapy water if required.

CLEANING

Clean all tools and equipment immediately after use with **Urochem 901**.

SAFETY

Contains organic solvents which are flammable. Do not use in confined spaces. Ensure adequate ventilation and the absence of any ignition source. Wear protective clothing. In case of eye contact wash well with water and obtain medical advice.

Please refer to product MSDS for further information.

APPROXIMATE COVERAGE

Joint Dimension:	LM per 600ml:
6 x 6mm	16.6
8 x 8mm	9.38
10 x 10mm	6
12 x 6mm	8.3
15 x 8mm	5



Urochem Trading (Pty) Ltd

Unit XP2, AEL Industrial complex, Cnr Ecqip and Weighbridge
Modderfontein, Gauteng; 1645

(+27) 11 608 2073 • www.urochem.co.za

Urochem 535

ONE-PART 35 SHORE A' HYBRID SEALANT AND ADHESIVE

TYPICAL PROPERTIES – AS PER UROCHEM QC

The below properties are based on in-house testing methodologies.

Mixing Ratio	Single component, use as supplied
Skin over time	Dependant on RH, temp & thickness
Practical Cure	± 2mm per day dependant on RH & temp
Hardness	± 5 Shore A
Movement accommodation	15%
Tensile strength	2,0 – 4 Mpa
Colour	Neutral – Colours available on request
Density	1.5 Cured
Shelf Life	12 Months, depending on storage conditions
Application Temp.	5 to 35°C
Service Temp.	60°C Dry & 50°C Wet
Pack Size	600ml sausages
Cleaning	Urochem 901
Storage	Store in a cool dry well ventilated place away from heat & sunlight

The information and recommendations relating to the application and end-use of **Urochem Trading (Pty) Ltd.** products, are given in good faith based on our current knowledge and experience of our products. **Urochem Trading (Pty) Ltd.** cannot accept any liability either directly or indirectly arising from the use of our products, as we have no direct or continuous control over where and how our products are stored and applied. Field service provided does not constitute supervisory responsibility. Users must test the efficacy of the product for their specific application, as no guarantee is expressed or implied. **Urochem Trading (Pty) Ltd.** reserves the right to change the properties of its products at any time without notice therefore users must always refer to the most recent issue of the specific Technical Data Sheet or contact one of our Technical Advisors before use.

FOR PROFESSIONAL USE ONLY



Urochem Trading (Pty) Ltd

Unit XP2, AEL Industrial complex, Cnr Ecqip and Weighbridge
Modderfontein, Gauteng; 1645

(+27) 11 608 2073 • www.urochem.co.za