

Urochem 611

HI-BUILD WATERPROOFING & CHEMICAL RESISTANT COATING

DESCRIPTION

Urochem 611 is a solvent free, two-part polyether-based coating. Designed as a 1,5mm seamless waterproofing coating available in both Natural, (not UV Stable) and Aluminium for UV stability. It yields an extremely flexible hi-build product with good chemical resistant and elongation properties.

PRODUCT APPLICATION

It is used as a 1,5mm seamless flexible waterproofing and chemical resistant coating on rooftops and in containment or banded areas where crack bridging of the substrate is essential. Can be used on both vertical and horizontal surfaces.

SURFACE PREPARATION

- The correct preparation of the surfaces is critical. All surfaces should be clean, sound, and dry, and all laitance or surface contamination should be removed by wire brushing, grinding or grit blasting. Vacuum or blow with compressed air to ensure total removal of dust.
- Moisture content of the substrate must be below 5%.
- All substrates must be prepared as detailed in Surface preparation above.
- Cementitious substrates must be primed with **Urochem 614** applied at 7 – 10m² per Lt (depending on porosity of the substrate).
- Bitumen substrates must be thoroughly cleaned, and all loose and friable material must be removed. Solvent wipe with **Urochem 901** and allow to dry before application of **Urochem 307** primer. (Applied at 6-8m² per Lt, may be overcoated within 1 Hour of application).

APPLICATION

Mix the activator and the base separately before adding the activator to the base and mixing thoroughly for a minimum of 3 minutes with a paddle mixer.

- Apply the correct primer as per data sheet. **Urochem 614** for concrete and **Urochem 307** for bituminous substrates.
- Apply 1st coat of **Urochem 611** to the primed substrate at approx. 1Lt per m² using a PU roller or a squeegee.
- Spike roll after 10 to 30 min to release any entrapped air and break the surface tension to assist with levelling.
- Apply 2nd coat of **Urochem 611** within 24 Hours at approx. 1Lt per m² using a PU roller or a squeegee.
- Spike roll after 10 to 30 min to release any entrapped air and to break the surface tension to assist with levelling.
- Leave to cure and open to traffic after 24 Hours.

CLEANING

Clean all tools immediately after use with **Urochem 901**. Once the material has polymerised it may only be removed mechanically.

SAFETY

Contains isocyanates. Ensure adequate ventilation. Do not use in confined spaces. Ensure adequate ventilation and the absence of any ignition source. Wear protective clothing. In case of eye contact wash well with water and obtain medical advice.



Urochem Trading (Pty) Ltd

Unit XP2, AEL Industrial complex, Cnr Ecqip and Weighbridge
Modderfontein, Gauteng; 1645

(+27) 11 608 2073 • www.urochem.co.za

Urochem 611

HI-BUILD WATERPROOFING & CHEMICAL RESISTANT COATING

TYPICAL PROPERTIES – AS PER UROCHEM QC

The below properties are based on in-house testing methodologies.

Mix Ratio	Mix as supplied – Do NOT SPLIT KITS
Pot Life	> 30min
Elongation	> 300%
Theoretical coverage	1,5 Lt / m ²
Shelf Life	6 Months, depending on storage conditions
Application Temp.	5 to 35°C
Service Temp.	-25 to +50°C
Pack Size	5 Lt, 10 Lt and 20 Lt kits
Colour	Natural and Aluminium
Chemical resistance	Please consult our technical department
Cleaning	Urochem 901
Storage	Store in a cool dry well-ventilated place away from heat & sunlight



Urochem Trading (Pty) Ltd

Unit XP2, AEL Industrial complex, Cnr Ecqip and Weighbridge
Modderfontein, Gauteng; 1645

(+27) 11 608 2073 • www.urochem.co.za

Urochem 611

HI-BUILD WATERPROOFING & CHEMICAL RESISTANT COATING

CHEMICAL COMPATIBILITY CHART

Chemical	% Conc
Acetic Acid	10%
Acetic Acid	25%
Ammonium Hydroxide Solution	0,88%
Ammonium Nitrate	50%
Ammonium Sulfate Solution	50%
Boric Acid Solution	saturated
Chromic Acid	10%
Citric Acid	20%
Formic Acid	40%
Hydrochloric Acid	conc
Lactic Acid	25%
Maleic Acid	30%
Nitric Acid	30%
Nitric Acid	70%
Phosphoric Acid	50%
Phosphoric Acid	90%
Sodium Hypochlorite	
Sodium hydroxide	30%
Sodium hydroxide	50%
Sugar solution	saturated
Sulphuric Acid	30%
Sulphuric Acid	70%
UREA	30%

The information and recommendations relating to the application and end-use of **Urochem Trading (Pty) Ltd.** products, are given in good faith based on our current knowledge and experience of our products. **Urochem Trading (Pty) Ltd.** cannot accept any liability either directly or indirectly arising from the use of our products, as we have no direct or continuous control over where and how our products are stored and applied. Field service provided does not constitute supervisory responsibility. Users must test the efficacy of the product for their specific application, as no guarantee is expressed or implied. **Urochem Trading (Pty) Ltd.** reserves the right to change the properties of its products at any time without notice therefore users must always refer to the most recent issue of the specific Technical Data Sheet or contact one of our Technical Advisors before use.

FOR PROFESSIONAL USE ONLY



Urochem Trading (Pty) Ltd

Unit XP2, AEL Industrial complex, Cnr Ecqip and Weighbridge
Modderfontein, Gauteng; 1645

(+27) 11 608 2073 • www.urochem.co.za